



COF EVALUATION DATA

Floor Finishes

Contact: American Decorative Concrete 120 Commercial Ave Lowell, AR 72745 (479) 725-0088	Test Performed By: Ben Jones <hr/> Time: 7:56 AM <hr/> Date: 1/8/10 <hr/> BOT Used: 1012
---	--

Zone	Description of Area Tested	Direction	SCOF	SCOF	SBR
			DRY James Leather	WET Neolite	DCOF DIN WET Rubber
1	Broom brushed concrete *Against grain	↑	0.75	0.99	*0.76
		→	*0.81	*1.00	0.79
2	Stained portion *Against grain 100 grit - Trowel finish concrete	↑	*0.72	*0.99	*0.65
		→	0.54	0.97	0.58
3	Color Juice Sealer 100 grit - Trowel finish	↑	0.82	0.99	0.65
		→	0.82	0.96	0.65
4	No Color 100 grit - Trowel finish	↑	0.64	0.90	0.67
		→	0.55	0.89	0.69
5	400 grit - polished	↑	0.65	0.87	0.76
		→	0.60	0.89	0.73
6	400 grit with color Defender	↑	0.76	0.91	0.67
		→	0.79	0.96	0.55
7	800 grit - polished	↑	0.66	0.93	0.77
		→	0.64	0.93	0.76
8	800 grit with color Defender	↑	0.81	0.86	0.64
		→	0.80	0.76	0.71
9	1500 grit	↑	0.65	0.92	0.79
		→	0.62	0.96	0.76
10	1500 grit with color Defender	↑	0.80	0.82	0.70
		→	0.83	0.82	0.70
11	3000 with color Defender and burnished with white pad	↑	0.75	0.85	0.63
		→	0.78	0.82	0.64
12	1500 grit color Defender burnished with white pad	↑	0.66	0.84	0.66
		→	0.64	0.86	0.61
13	800 grit with color Defender burnished with white pad	↑	0.75	0.87	0.59
		→	0.79	0.88	0.55
14	400 grit with color Defender burnished with white pad	↑	0.71	0.87	0.51
		→	0.73	0.96	0.74