

Category > Protect

SR² Plus

Fully Penetrating Stain Resistor



Product Description

Ameripolish® SR² Plus is a penetrating stain repellent specifically formulated to protect polished, dyed and non-dyed concrete from oil and water-based stains. The water and oil repelling qualities of SR² Plus provides superior stain protection on most substrates. SR² Plus can be used as a standalone product but, to obtain optimum performance, Ameripolish® SR² Plus is recommended for use with Ameripolish® 3D HS or HSL Densifiers.

Features

- Non-topical, penetrating sealer
- Darkens/Enriches the surface color
- Increases both gloss and DOI readings
- Treated surfaces 'breathe' and do not trap moisture
- Excellent stain repellency for residential, commercial, and even industrial applications
- Extreme hydrophobic and oleophobic characteristics for maximum stain resistance
- Safe for surfaces that experience high traffic
- Compatibility to bond with Ameripolish Color System components to protect color in slab
- Provides a chance to clean up spills before they stain or etch a surface
- Same familiar application method

Uses

Ameripolish® SR²™ Plus is ideal to be used on:

- New or existing polished concrete
- Exposed concrete flooring

Dilution & Coverage

Ameripolish® SR²™ Plus is shipped Ready to Use (RTU) and should not be mixed with any other chemical. Approximate coverage rate is 3,000 - 5,000 sqft per gallon.

Preparation

Thoroughly clean the surface that Ameripolish® SR² Plus is to be applied to, removing all oil, dirt, and other contaminants. Vacuum and clean the surface with auto-scrubber and fresh water, allowing it to dry thoroughly. Caulking, patching, and

Product Specification

Application:	Spray and Ameripolish® Microfiber Pad
Appearance:	Clear
VOC:	Compliant (5g/l)
Shelf life:	1 year
Solvent:	Proprietary (non-hazardous)

Packaging Specification

Product #	Shipping Wt.	Container
sr2plus-1	10 lbs.	1 gallon RTU
sr2plus-5	50 lbs.	5 gallons RTU
sr2plus-30	300 lbs.	30 gallons RTU
sr2plus-55	550 lbs.	55 gallons RTU
sr2plus-250	2,500 lbs.	250 gallons RTU



Category > Protect

SR² Plus

Fully Penetrating Stain Resistor



joint sealants should be installed before application, or joint preparation will be needed to ensure caulk adhesion. This product will not prevent water penetration through structural cracks, defects, or open joints. Surfaces should dry for proper penetration.

Application

Prior to starting, apply SR² Plus to sample area of each type of concrete to be treated, using application procedures proposed for the project. Confirm that concrete is receptive to SR² Plus. 3D HS™ or 3D HSL™ is recommended to expand SR² Plus coverage rates and add stain resistance. Preferred method of application is with a pump sprayer fitted with Green #4 or similar conical mist tip with 4.2 gal/hr flow at 40psi, (15.9 L/hr at 275.8 kPa) and an Ameripolish® microfiber pad.

Ambient temperature should be 40-90°F (4-32°C) during application. Do not apply over 90°F (32°C); avoid application on hot, windy days. SR² Plus provides the best protection when applied in a light "film" coat.

1. Spray a light mist of SR² Plus onto concrete surface and immediately spread evenly with Ameripolish® microfiber pad. Apply enough material to keep the surface wet for about a minute before penetrating; attain 100% coverage, without either dry streaking or puddling.
2. Mop out any puddles thoroughly until they completely penetrate the surface.
3. NOTE: For Vertical Surfaces apply enough material to thoroughly wet the surface in a uniform application. Do not allow rundown below the spray pattern.
4. Burnish with a high-speed burnisher, fitted with an Ameripolish® G3 pad, or auto-scrub with white pad to remove surface haze.
5. Chemical resistance gains strength over time. Avoid etching agents for seven days if possible. Areas that will be exposed to excessive, ongoing spills or extremely porous substrates may benefit from a second application of SR² Plus before burnishing.

Next Steps

Floor is ready for light foot traffic when SR² Plus is dry to touch;

protect treated surfaces from traffic for at least one hour. SR² Plus gains its chemical resistance and water repellency after 24 hours, and it cures fully within seven days. However, even after becoming densified and polished, concrete is still a porous substrate.

Cleanup

Clean tools and equipment immediately with mineral spirits or equivalent cleaning solvent. Always remove rundown and spills immediately.

Storage

- Store upright in safe dry place at 40-110F° (4 -43C°)
- Keep product from freezing
- Keep out of reach of children
- Seal container after use
- Do not mix with other chemicals

VOC Compliance

In addition, Ameripolish® SR²™ offers VOC compliance with low VOC at 5g/L and is also compliant with national, state and district regulations:

- US Environmental Protection Agency
- California Air Resources Board SCM Districts*
- South Coast Air Quality Management District*
- Maricopa County, AZ
- Northeast Ozone Transport Commission*

*Before application, verify product conformance with local and state codes.

Warning & Safety Information

KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY. BEFORE USING THIS PRODUCT PLEASE READ THE SAFETY DATA SHEET IN ITS ENTIRETY! Safety Data Sheets (SDS) can be found online at www.ameripolish.com or upon request by contacting Ameripolish at 1-800-592-9320.

SURFACES MUST BE CLEAN AND DRY BEFORE APPLICATION

Category > Protect

SR² Plus

Fully Penetrating Stain Resistor



OF THE PRODUCT. NEW SLABS MUST HAVE CURED FOR AT LEAST 28 DAYS BEFORE APPLICATION. For best results perform a moisture content test on both newly-poured and existing slabs. Slabs with a moisture content of 5 lbs per foot or less show best performance (calcium chloride test per ASTM F1869.) High moisture levels may affect performance of product. Do not apply if concrete is frozen, dirty, or has standing water. Test surface absorbency with a light water spray – concrete surface should wet uniformly. If concrete does not wet uniformly, remove any surface contaminants with appropriate cleaning treatment or mechanical process.

Warranty

The information contained herein is believed to be reliable. This information is based on laboratory testing and results. Because of variations in methods, conditions and equipment, each user must test this product to make a judgment of performance. Applicator is responsible for testing material for effectiveness and performance. Manufacturer obligation is limited to the refund of purchase price or replacement of material if proven to be defective. Claims must be made in writing and received within one year from date of product sale to original buyer. Sole remedy shall be replacement of product proven defective.