

(All abrasive steps are cut wet)

Standard Process



Step	Grit Equivalent
● 00	40
● 0	100
● 1	400
● 2	800
● 3	1500

~For soft concrete add an additional densification step before the 00's~
~If transitioning from metals, switch to 00 after to 50 grit~